

## **Z-Ultimate 4000T High-Tack**

# Thermal transfer, gloss polyester label with a high-performance permanent acrylic adhesive

This thermal transfer gloss polyester label features a high-tack permanent acrylic adhesive, providing exceptional smear and scratch resistance. With excellent durability and chemical resistance, it is well-suited for demanding applications. The label's topcoating is designed for fanfolding, adding flexibility in usage. It complies with FDA 175.105 requirements for indirect food contact, making it appropriate for food-related environments. Available in white (65300RM) and silver (66447RM), this label offers reliable performance and versatility for various labeling needs.



#### **UL Certified Labeling Solution**

UL Certified labeling solution Z-Ultimate 4000T High-Tack white and silver labels, combine with the 5095 and 5100 ribbons have been fully tested and certified by UL. In addition, Zebra Supplies manufacturing plants are authorized to pre-print the UL mark.

#### **Customization Available**

Zebra can deliver Z-Ultimate 4000T High-Tack labels multiple configurations to support your business needs.

#### **Features**

- Thermal transfer, gloss polyester label with a high-tack permanent acrylic adhesive
- Unparalleled smear/scratch resistance
- Excellent durability and chemical resistance
- Topcoating is suitable for fanfolding
- Meets FDA 175.105 for indirect food contact requirements
- Available in white (65300RM) and silver (66447RM)

### **Specifications**

Material Construction	
Facestock	White, silver, or clear coated polyester. Caliper 2.3 mil
Adhesive	High-tack, acrylic-based Caliper 2.0 mil
Liner	50 lb. semi-bleached, kraft stock. Caliper 3.2 mil
Facestock Tensile S	trength
Machine Direction	18,000 psi
Transverse Direction	22,000 psi
Temperature Perfo	rmance
Minimum Application Temperature	50° F (10° C)
Service Temperature	-40° F to 302° F -40° C to 150° C
Optimal Storage Conditions	72° F (22° C) at 50% RH
Expected Exterior Life	3 years
Chemical Resistance	e
Weak	
Blood	Recommended
Body Fluid	Recommended
Salt Water	Recommended
Water	Recommended
Window Cleaner	Recommended
Moderate	
Alcohol	Recommended
Ammonia	Recommended
Bleach	Recommended
IPA	Recommended
Harsh	
Gasoline	Test in Your Application
Grease	Test in Your Application
Oil	Test in Your Application
Extreme	
Acetone	NR
IR Reflow	NR
MEK	NR
TCE	NR
Xylene	NR

Adhesive Strength 180 Degree Peel Adhesion (oz/in)	
Stainless Steel	Initial 5 min: 90
	Final 24 h: 105
Polycarbonate	Initial 5 min: 30
	Final 24 h: 85
Polyethylene	Initial 5 min: 30
	Final 24 h: 35
·	

#### **Regulatory Compliance**

Z-Ultimate 4000T High-Tack white and silver with 5095 and 5100 ribbons is UL/cUL-recognized for indoor/outdoor use.

All products should be pre-tested to ensure it meets all intended requirements of specific end-use applications

#### Markets and Applications

- Automotive Labelling
- Product Identification
- Product Labelling

